

Armaflex® 520 BLV Adhesive

Fiber Free

A black, low VOC air-drying contact adhesive that is excellent for joining seams and butt joints of Armaflex Pipe and Sheet Insulations



- Formulated for Armaflex Insulations
- Developed to meet SCAQMD RULE 1168
- Hexane-free, Toulene-free, contact adhesive
- Proven: no gapping, no tape needed

 armacell®



Technical Data: Armaflex 520 BLV Adhesive

Description:

A black, low VOC air-drying contact adhesive that is excellent for joining seams and butt joints of Armaflex Pipe and Sheet Insulations

Specifications Compliance:

Meets South Coast Air Quality Management District (SCAQMD) Rule 1168

Approvals, Certifications, Compliances:

- All Armacell facilities in North America are ISO 9001:2008 certified.

Typical Properties

Specifications:	Values	
Color:	Black	
Net Weight:	6.9 pounds per gallon (828 g/l)	
Composition:	Synthetic rubber base with synthetic resins and fillers added; hydrocarbon- and ketone-type solvents.	
Volatile Organic Compounds (VOC) Content:	Zero V.O.C. g/l calculated SCAQMD 1168 and EPA Method 24	
Solids Content	Approximately 30% by weight	
Coverage	200 sq ft (5m2/l) per gallon max, single coat (depending upon porosity of materials bonded and air temperature)	
Shelf Life	1 year in original sealed container; storage temperature 60°F to 80°F (16°C to 27°C)	
Temperature Limits	250°F (120°C) – Armaflex Pipe Insulation seams and joints	
Dry Time Before Bonding	3-5 minutes depending on ambient conditions	
Bond Time	3-6 minutes	
Full Cure Time	36 hours	
Container Sizes	Pint brush-top cans and gallon containers	
Wet Flash Point	Below -4°F (-20°C) (TOC)	ASTM E 84
Flame Spread and Smoke Developed Index:	25/50 rated	
Minimum Application Temperature:	40°F (4°C)	

ARMACELL LLC

TEL: 800.866.5638

FAX: 919.304.3847

info.us@armacell.com

www.armacell.us

7600 Oakwood Street Extension, Mebane, NC 27302



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice.